



Ürün ve Uygulamalar

Shinox, hızlı temizleme etkisi ve mükemmel dayanıklılığa sahip paslanmaz çelik bilyelerimizdir. Shinox ile yapılan kumlama işlemi çok az toz oluşturur ve yüzeye parlak bir görünüm kazandırır. Bu malzeme, kaplama öncesi yüzey hazırlığı, çapak alma ve kireç giderme işlemlerinde tekerlekli kumlama makinelerinde kullanılır.

Kullanım Alanları

- Hızlı Temizlik
- Yüzey Parlatma
- Kaplama Hazırlığı
- Çapak/Kireç Giderme

Fiziksel özellikler

Tahıl Şekli : Küresel
Renk : Gri
Sertlik : 220 - 350HV
Mikroyapı : östenitik
Yoğunluk : Yaklaşık 7,0 g/cm³
Yığın Yoğunluğu : Yaklaşık 4,1 g/cm³

Ambalajlama

- Euro palet üzerinde 25 kg'lık çuvallar.
- 500 kg/ 1000 kg
- Minimum sipariş miktarı 25 kg.

Kimyasal Bileşim

Krom	Silikon	Karbon	Manganez	Nikel
18%	2%	0.20%	1%	8%

Products and Applications

Shinox is our stainless steel shot with a fast cleaning action and excellent durability. Blasting with Shinox creates only little dust and gives a bright appearance to the surface. The material is used in wheel blast machines for surface preparation prior to coating, deburring and descaling.

Areas of Application

- Quick Cleaning
- Surface Polishing
- Coating Preparation
- Deburring / Scale Removal

Physical characteristics

Grain Shape : Global
Color : Gray
Hardness : 220 - 350HV
Microstructure : Austenitic
Density : Approx. 7.0 g/cm³
Bulk Density : Approx. 4.1 g/cm³

Packaging

- Euro palet üzerinde 25 kg'lık çuvallar.
- 500 kg/ 1000 kg
- Minimum sipariş miktarı 25 kg.



Beden Tablosu / Size Chart

	AS 200	AS 150	AS 100	AS 90	AS 60	AS 50	AS 40	AS 30	AS 20	AS 10
4.00 mm	0									
3.35 mm	10 mak.									
2.80 mm		0								
2.36 mm		10 mak.								
2.00 mm			0							
1.70 mm	90 min.		20 mak.	0						
1.40 mm				5 mak.	0					
1.18 mm		90 min.			20 mak.	0				
1.00 mm						5 mak.	0			
0.85 mm			90 min.	90 min.						
0.71 mm					90 min.		20 mak.			
0.60 mm						85 min.		0		
0.42 mm							90 min.	20 mak.	0	
0.30 mm									10 mak.	
0.25 mm										0
0.15 mm								90 min.		10 max
0.075 mm									90 min.	
0.045 mm										90 min.

